

Hiiharjalaadut

SGL CARBON Corporation, St. Marys

Laatu- merkintä	Ominai- vastus	Tiheys	Taivutus- lujuus	Kovuus	Jatkuva- virtatiheys	Kehä- nopeus	
	$\mu\Omega\text{m}$	g/cm^3	Mpa	Shore	A/cm^2	m/s	
Sähkögrafitti	E3	8	1,69	21	30	12	45
	E31	48	1,60	28	70	12	40
	E37	43	1,60	34	75	10	40
	E41	58	1,55	21	60	12	45
	E44	43	1,72	38	80	10	35
	E45	58	1,55	23	55	12	45
	E49	43	1,64	21	70	12	50
	E57	53	1,53	18	50	12	45
	E60	48	1,66	37	75	12	50
	E61	15	1,45	10	30	12	45
	E63	14	1,58	14	30	12	50
	4029	64	1,46	14	45	12	40
	4041	76	1,49	9	50	12	37
	6677	76	1,60	17	65	12	50
Luonnongrafitti	702	25	1,43	5	15	10	70